

Paint Finishing Standard within the Industry



STANDARD OF PAINTING

Coatings used are to be suitable for the relevant conditions and relevant wear and tear. Unless documented otherwise, painting is defective if it does not comply with the manufacturer's installation instructions or AS/NZS 2311 – Guide to the painting of buildings.

SURFACE FINISH OF PAINTWORK

Paintwork is defective if application defects or blemishes such as paint runs, paint sags, wrinkling, dust, bare or starved painted areas, colour variations, surface cracks, irregular and coarse brush marks, sanding marks, blistering, uniformity of gloss level and other irregularities in the surface that are visible from a normal viewing position.

Excessive over-painting of fittings, trims, skirting, architraves, glazing and other finished edges is a defect.

NAIL AND SCREW FIXINGS

Fixings of unfilled depressions caused by fixings are defects in painted or stained surfaces if they can be seen from a normal viewing position.

MECHANICAL DAMAGE AND NATURAL DEFECTS IN SURFACES

Holes and any other unfilled depressions in painted or stained timber surface defects caused by mechanical damage, natural characteristics such as gum pockets or surface splits are defects if they can be seen from a normal viewing position.

PAINT DURABILITY

Unless documented otherwise, coatings are defective if they fail by lifting, blistering, flaking, fading etc. within the minimum period shown in table below.

MINIMUM DURABILITY OF COATED FINISHES

COATING	MINIMUM DURABILITY
Exterior Acrylic	36 months
Exterior Enamel	24 months
Exterior semi-transparent stains	12 months
Exterior clear finishes not recommended	
Interior – all finishes	36 months

All preparation and painting works should be to the AS 2311:2017 Painting of Buildings

Master Painters NZ Association Po Box 40355 Upper Hutt 5140– PH 04 472 5870

Email nationaloffice@masterpainters.org.nz www.masterpainters.co.nz